

**University of Mosul**  
**College of Dentistry**



**Evaluation of Nickel and Chromium Ions Release  
from Orthodontic Archwires after Using  
Magnetized Water as a Mouthrinse: A  
Comparative Study**

**A Thesis Submitted by**

**Zinah Natheer Saeid Al Zubaidy**

**To**

**the Council of College of Dentistry**

**University of Mosul**

**as a Partial Fulfillment of the Requirements**

**for the Degree of Master of Science in**

**Orthodontics**

**Supervised by**

**Asst. Prof. Dr. Afrah Khazal Al Hamdany**

---

**ABSTRACT**

**Aims:** The aims of current study were to evaluate the release of nickel and chromium ions from stainless steel and nickel titanium orthodontic archwires which immersed in magnetized water with different magnetic powers and different immersion times, in addition to study the surface topography of orthodontic archwires after immersion in magnetized water.

**Materials and Methods:** The samples used in this study were consist of two hundreds (1.5" x 0.25") as received orthodontic stainless steel and nickel titanium archwires. The archwires were divided into four main groups according to the used mouthrinse as follows: magnetized water prepared at high power magnetic field group, magnetized water prepared at low power magnetic field group, Ortho Kin group (positive control) and distilled water group (negative control). Each main group was sub divided further into two sub groups: (1.5" x 0.25") stainless steel orthodontic archwires and (1.5" x 0.25") nickel titanium orthodontic archwires. Each sub group contain five time points intervals (24hours, 1week, 2weeks, 3weeks and 4weeks). Five archwires were used for each time interval. The nickel and chromium released were measured at the different time intervals (24hours, 1week, 2weeks, 3weeks and 4weeks) by using Atomic Absorption Spectrometer. The surface topography of orthodontic archwires were examined with Scanning Electron Microscope and Atomic Force Microscope. Statistical analysis was done using SPSS Statistics, V26. Data were analyzed with multiple comparison one-way ANOVA and pairwise comparison Duncan's Multiple Range Test and the significant level was evaluated at  $P \leq 0.05$ .

**Results:** The results of this study showed that magnetized water prepared at both high and low magnetic field powers had significantly less amounts of

nickel and chromium ions release from stainless steel orthodontic archwires and also less amount of nickel ion release from nickel titanium orthodontic archwires when compared with Ortho Kin mouthrinse group. And the surface topography of NiTi and SS archwires immersed in MW was less affected from those immersed in OK.

**Conclusions:** The study concluded that the magnetized water could be used as an alternative to other commercially available mouthrinses (as Ortho Kin) during orthodontic treatment.



جامعة الموصل  
كلية طب الأسنان

# تقييم انبعاث أيونات النيكل والكروم من الأسلاك المقوسة التقويمية بعد استخدام الماء الممغنط كغسول للفم (دراسة مقارنة)

رسالة تقدمت بها

زينة نذير سعيد الزبيدي

الى مجلس كلية طب الأسنان / جامعة الموصل  
كجزء من متطلبات نيل شهادة الماجستير في اختصاص  
تقويم الاسنان

بإشراف

أ.م.د. أفراح خزل الحمداني

## الخلاصة

**الأهداف:** هدفت الدراسة الحالية إلى معرفة تأثير استخدام الماء الممغنط كغسول للفم سيؤثر على إنبعاث أيونات النيكل والكروم من أسلاك تقويم الأسنان الفولاذية المقاومة للصدأ واسلاك النيكل تيتانيوم، ومقارنة تأثيرات الماء الممغنط المعرض لقوة مجال مغناطيسي مختلفة و أوقات غمر مختلفة على إنبعاث أيونات النيكل والكروم، بالإضافة إلى دراسة خصائص السطح للأسلاك المقوسة المغمورة في الماء الممغنط.

**المواد وطرائق العمل:** نفذت هذه الدراسة على ٢٠٠ من الأسلاك المقوسة ذات المقطع العرضي (٠,١٦x٠,٢٢) تم تقسيم الأسلاك المقوسة إلى أربع مجموعات رئيسية وفقاً لغسول الفم المستخدم على النحو التالي: مجموعة الماء الممغنط المحضر في مجال مغناطيسي عالي الطاقة، مجموعة الماء الممغنط المحضر في مجال مغناطيسي منخفض الطاقة، مجموعة غسول الفم اورثوكين ومجموعة الماء المقطر. تم تقسيم كل مجموعة رئيسية إلى مجموعتين فرعيتين: (٠,١٦x٠,٢٢) أسلاك تقويم الأسنان من النيكل تيتانيوم. تحتوي كل مجموعة على خمس فترات زمنية (٢٤ ساعة، أسبوع، أسبوعان، ٣ أسابيع و٤ أسابيع). تم استخدام خمسة أسلاك مقوسة لكل فترة زمنية. تم قياس أيونات النيكل والكروم المنبعثة من أسلاك التقويم في الفترات الزمنية المختلفة باستخدام مطياف الامتصاص الذري (BUCK Scientific, USA) وتم فحص الخصائص السطحية للأسلاك المقوسة باستخدام المجهر الإلكتروني الماسح (TESCAN MIRA<sup>3</sup>, French) وتم فحص خشونة السطح باستخدام مجهر القوة الذرية (NaioAFM Nanosurf Switzerland). تم إجراء التحليل الإحصائي باستخدام برنامج (SPSS Statistics, V٢٦) وتم تحليل البيانات باستخدام الانوفا واختبارات المدى المتعددة لدانكان.

**النتائج:** أظهرت النتائج تسجيل كمية أقل بكثير من أيونات النيكل والكروم المنبعثة من أسلاك تقويم الأسنان الفولاذية المقاومة للصدأ ومن أيونات النيكل المنبعثة من أسلاك تقويم الأسنان المقوسة من النيكل تيتانيوم في محاليل الماء الممغنط بالمقارنة مع مجموعة غسول الفم اورثوكين.

**الاستنتاجات:** يمكن استخدام الماء الممغنط كبديل للعديد من غسولات الفم التجارية المتوفرة في الأسواق مثل اورثوكين خلال فترة تقويم الأسنان.