

**University of Mosul**  
**College of Dentistry**



**Evaluation the Effect of Incorporated  
Hydroxyapatite Prepared from Dried Egg Shell  
on Some Properties of Relined Denture Base**

**A Thesis Submitted by  
Zena Joma Hassan AL-Bahar**

**To  
The Council of College of Dentistry  
Mosul University  
In a Partial Fulfillment of the Requirements  
For the Degree of Master of Science  
In  
Prosthodontics**

**Supervised by**

**Nadira A. Hatim  
Professor**

**Dr. Amer A. Taqa  
Professor**

---

**2013A.D.**

**1434 A.H.**

## ABSTRACT

**Objective:** Hydroxyapatite (HA)  $[\text{Ca}_{10}(\text{PO}_4)_6(\text{OH})_2]$  was used in various biomedical fields such as dental material, bone substitute and hard tissue paste. Hydroxyapatite (HA) reinforced polymer have many potential clinical applications like bone cement, dental implants, coating of joint replacement prosthesis (Tham and Chow, 2010).

So the aims were to determine the effect of incorporation of recently synthesized Hydroxyapatite from egg shell in different concentration on dimensional accuracy, transverse strength, FTIR of RESPAL NF heat cured acrylic denture base, with, and without relining, and biocompatibility test on rabbit.

**Materials and Methods:** 171 samples of heat cured acrylic resin (HCAR) were prepared, and divided into five groups; the 1<sup>st</sup> group (Control) heat cured acrylic resin, the 2<sup>nd</sup> groups heat cured acrylic resin mixed with 2% of Hydroxyapatite (HA), the 3<sup>rd</sup> groups (HCAR) relined with 2% (HA), the 4<sup>th</sup> group (HCAR) mixed with 5% of Hydroxyapatite, and the 5<sup>th</sup> group (HCAR) relined with 5% of Hydroxyapatite.

The samples were tested after 48 hours from preparation for (biocompatibility tests through implantation of samples in subcutaneous layer of the mandible of the local bred rabbit, FTIR test, microscopical examination of Hydroxyapatite, indentation hardness, transverse strength, water sorption and solubility, tensile strength, dimensional accuracy, residual monomer.

**Results:** showed significant differences in the transverse strength, no residual monomer release, no dimensional changes after adding Hydroxyapatite to (HCAR). FTIR spectra of pure poly methyl methacrylate (PMMA), and the (PMMA) with Hydroxyapatite extracted from egg shells showed no difference in the peaks before, and after

addition of Hydroxyapatite to the polymer. Results of implantation samples showed increased bone formation.

**Conclusions:** after adding Hydroxyapatite to heat cured acrylic resin showed an increase in strength of denture base with high dimensional accuracy, good biocompatibility with new bone formation in both 2%, and 5% Hydroxyapatite. FTIR spectra of polymer with and without Hydroxyapatite showed homogeneous distribution which will improve the mechanical properties of heat cured acrylic resin.



جامعة الموصل  
كلية طب الأسنان

قياس تأثير إضافة مادة الهيدروكسي ابيتايت المحضر من قشور  
البيض الجاف على بعض خواص مادة طقم الأسنان المبطن

رسالة تقدمت بها

زينة جمعة حسن البهار

إلى

مجلس كلية طب الأسنان

جامعة الموصل

كجزء من متطلبات نيل شهادة الماجستير

في

صناعة الأسنان

بإشراف

الأستاذ الدكتور

عامر عبد الرحمن طاقة

الأستاذ

نادرة عبد الرضا حاتم

## الخلاصة

البوليمر المعزز بمادة الهيدروكسي ابيتايت لديها العديد من التطبيقات السريرية المحتملة مثل اسمنت العظام، زراعة الأسنان، واستبدال المفاصل في الجراحة الترميمية. لم يتم إدراج تأثير هيدروكسي ابيتايت مع الراتنج الاكريلي من قبل.

لذلك كانت الأهداف لتقييم تركيز وتأثير إدماج الهيدروكسي ابيتايت الاصطناعية مؤخرًا من قشرة البيضة على دقة الأبعاد، وقوة عرضية، FTIR لقاعدة الاكريليك من نوع RESPAL NF، مع، ودون إعادة تطيينها، واختبار التوافق الحيوي على الأرانب. تم إعداد ١٧١ عينة من راتنج الاكريليك، وتنقسم إلى ثلاث مجموعات، والمجموعة الأولى (التحكم)، ومجموعات الثانية والثالثة مع إضافات ٢٪ و ٥٪ من هيدروكسي ابيتايت.

تم تقسيم المجموعات الثانية والثالثة إلى مجموعتين فرعيتين؛ {الأولى: راتنج الاكريليك مختلطة مع ٢٪، أو ٥٪ من هيدروكسي ابيتايت}، والثاني: راتنج الاكريليك مبطن مع إضافات من ٢٪ أو ٥٪ هيدروكسي ابيتايت}. تم اختبار العينات بعد ٤٨ ساعة (قوة عرضية، دقة الأبعاد، مونومر المتبقية، FTIR، واختبارات التوافق الحيوي، من خلال زرع العينات في طبقة تحت الجلد للفك السفلي من الأرانب ولدت محليا. أظهرت النتائج فروق ذات دلالة إحصائية، مع زيادة في القوة عرضية، لا إطلاق مونومر المتبقية، لا يوجد أي تغييرات في الأبعاد بعد إضافة هيدروكسي ابيتايت الى راتنج الاكريليك. وأظهرت FTIR أطياف بولي ميثايل ميثاكريليت نقية، وبولي ميثايل ميثاكريليت مع هيدروكسي ابيتايت المستخرجة من قشر البيض لا يختلف في المرتفعات، قبل، وبعد إضافة هيدروكسي ابيتايت إلى البوليمر. وأظهرت نتائج عينات الزرع زيادة تكوين العظام. الاستنتاجات بعد إضافة هيدروكسي ابيتايت الى الراتنج الاكريليك أظهرت زيادة في قوة قاعدة أسنان مع دقة الأبعاد عالية، التوافق الحيوي جيدة مع تكوين العظام الجديدة في كل من ٢٪، وهيدروكسي ابيتايت ٥٪. وأظهرت FTIR أطياف البوليمر دون ومع هيدروكسي ابيتايت توزيع متجانس التي من شأنها تحسين الخواص الميكانيكية لراتنج الاكريليك.