

University of Mosul
College of Dentistry



**Effects of Nano-Chitosan loaded with Calcium Phosphate
and Gallic Acid Bioactive Materials for Enhancement of
Enamel Remineralization on Some Properties of
Orthodontic Adhesive Primer**

A Dissertation Submitted by

Lara Riyadh Abdulraheem Al-Banaa

To

The Council of College of Dentistry

University of Mosul

as a partial Fulfillment of the Requirements

for the Degree of Philosophy Doctorate

In

Dental Sciences

Supervised by

Prof. Dr.

Ali Rajih Mahmood

Prof. Dr.

Fawzi Habeeb Jabrail

ABSTRACT

Background: One of the most undesirable complications of comprehensive orthodontic treatment is the development of white spot lesions. Despite various preventive measures, their prevalence remains notably high at the time of brackets removal. Therefore, it is crucial to inhibit cariogenic bacterial activity while promoting enamel remineralization to effectively prevent and manage white spot lesions.

Aims: The aim of this study is to prepare and evaluate the effects of incorporating nano-chitosan loaded with bioactive materials (calcium phosphate and gallic acid alone or in combination) into orthodontic adhesive primer as an antimicrobial and remineralizing agent while preserving the physical, mechanical and chemical properties of orthodontic adhesive.

Materials and Methods: Nano-chitosan loaded with bioactive materials (tricalcium phosphate alone, gallic acid alone, and a combination of both) were prepared and incorporated into Transbond™ XT primer at 5% and 10 % by weight concentration to form a modified adhesive primer. The prepared materials were characterized by Fourier Transform Infrared spectroscopy (FTIR) and Field Emission Scanning Electron Microscopy (FESEM) coupled with Energy-Dispersive X-ray spectroscopy (EDX). This study have seven groups: Group 1: (control group), group 2: (5% nano-chitosan/calcium phosphate primer), group 3: (10% nano-chitosan/calcium phosphate primer), group 4: (5% nano-chitosan/gallic acid primer), group 5: (10% nano-chitosan/gallic acid primer), group 6: (5% nano-chitosan/calcium phosphate+ gallic acid primer), group 7: (10% nano-chitosan/calcium phosphate+ gallic acid primer). The control and modified primer groups were characterized using FTIR and FESEM. Further assessments included shear bond strength testing and analysis of bonding failure modes, evaluation of the degree of monomer conversion, wettability, and the release


behavior of gallic acid and calcium phosphate. Antibacterial properties were investigated against *Streptococcus mutans* and *Lactobacillus acidophilus*. Remineralization of demineralized enamel was assessed using FESEM/EDX to detect mineral precipitation, analyze the shape of hydroxyapatite crystals, and measure the calcium and phosphate weight percentages along with the Ca/P ratio. Statistical significance was set at $p \leq 0.05$.

Results: The FTIR and FESEM/EDX analysis showed a successful preparation and loading of chitosan hydrogel with the bioactive materials. The orthodontic adhesive primer exhibited no chemical or structural changes upon the addition of nano-chitosan loaded with bioactive materials (calcium phosphate and gallic acid) and were homogeneously distributed within it. The results of shear bond strength and the degree of monomer conversion showed an increase in their values, with significant differences among the groups. However, no significant differences were observed regarding the adhesive remnant index and contact angle measurements. Additionally, modified orthodontic primer showed significant antibacterial activity against cariogenic *Streptococcus mutans* and *Lactobacillus acidophilus* particularly in the 10 % nano-chitosan/ calcium phosphate+ gallic acid primer group. Moreover 5 % nano-chitosan/ calcium phosphate+ gallic acid primer group showed the greatest calcium and phosphate weight percentage and Ca/P ratio than other groups. The release of calcium phosphate and gallic acid from the modified primer showed a slow and sustained release over four weeks, with a significant difference between the 5% and 10% groups at each weekly interval. The release of bioactive materials confirmed the antibacterial and remineralizing effects of the modified primer groups.

Conclusions: All orthodontic primer groups modified with nano-chitosan loaded with bioactive materials exhibited antibacterial and remineralizing properties. They also enhanced the physical, mechanical, and chemical adhesive properties. Among them, the primer containing 10% nano-chitosan/calcium phosphate with gallic acid showed the strongest antibacterial activity. In contrast, the 5% nano-chitosan/calcium phosphate with gallic acid primer showed the highest mineral contents, making it the most suitable option for enamel remineralization.

Effects of Nano-Chitosan loaded with Calcium Phosphate and Gallic Acid Bioactive Materials for Enhancement of Enamel Remineralization on Some Properties of Orthodontic Adhesive Primer

Author: Lara Riyadh Abdulraheem Al-Banaa **Advisor:** Prof. Dr. Ali Rajih Mahmood & Prof. Dr. Fawzi Habeeb Jabrail **Publisher:** University of Mosul

HIGHLIGHTS	GRAPHICAL ABSTRACT
- The study highlighted the remineralization and antibacterial effects orthodontic primer modified with nano-chitosan loaded with bioactive materials - The primer containing 10% nano-chitosan/calcium phosphate with gallic acid showed the strongest antibacterial activity. - The 5% nano-chitosan/calcium phosphate with gallic acid primer showed the highest mineral contents,	
Keywords: Antibacterial Chitosan Gallic acid Orthodontics Remineralization Tricalcium phosphate White spot lesions	ABSTRACT Aims: The aim of this study is to prepare and evaluate the effects of incorporating nano-chitosan loaded with bioactive materials (calcium phosphate and gallic acid alone or in combination) into orthodontic adhesive primer as an antimicrobial and remineralizing agent while preserving the physical, mechanical and chemical properties of orthodontic adhesive. Materials and Methods: Nano-chitosan loaded with bioactive materials (tricalcium phosphate alone, gallic acid alone, and a combination of both) were prepared and incorporated into Transbond™ XT primer at 5% and 10 % by weight concentration to form a modified adhesive primer. The prepared materials were characterized by Fourier Transform Infrared spectroscopy (FTIR) and Field Emission Scanning Electron Microscopy (FESEM) coupled with Energy-Dispersive X-ray spectroscopy (EDX). This study have seven groups: Group 1: (control group), group 2: (5% nano-chitosan/calcium phosphate primer), group 3: (10% nano-chitosan/calcium phosphate primer), group 4: (5% nano-chitosan/gallic acid primer), group 5: (10% nano-chitosan/gallic acid primer), group 6: (5% nano-chitosan/ calcium phosphate+ gallic acid primer), group 7: (10% nano-chitosan/ calcium phosphate+ gallic acid primer). The control and modified primer groups were characterized using FTIR and FESEM. Further assessments included shear bond strength testing and analysis of bonding failure modes, evaluation of the degree of monomer conversion, wettability, and the release behavior of gallic acid and calcium phosphate. Antibacterial properties were investigated against Streptococcus mutans and Lactobacillus acidophilus. Remineralization of demineralized enamel was assessed using FESEM/EDX to detect mineral precipitation, analyze the shape of hydroxyapatite crystals, and measure the calcium and phosphate weight percentages along with the Ca/P ratio. Statistical significance was set at $p \leq 0.05$. Results: The results of shear bond strength and the degree of monomer conversion showed an increase in their values, with significant differences among the groups. However, no significant differences were observed regarding the adhesive remnant index and contact angle measurements. Additionally, modified orthodontic primer showed significant antibacterial activity against cariogenic Streptococcus mutans and Lactobacillus acidophilus particularly in the 10 % nano-chitosan/ calcium phosphate+ gallic acid primer group. Moreover 5 % nano-chitosan/ calcium phosphate+ gallic acid primer group showed the greatest calcium and phosphate weight percentage and Ca/P ratio than other groups. The release of calcium phosphate and gallic acid from the modified primer showed a slow and sustained release over four weeks, with a significant difference between the 5% and 10% groups at each weekly interval. The release of bioactive materials confirmed the antibacterial and remineralizing effects of the modified primer groups. Conclusions: All orthodontic primer groups modified with nano-chitosan loaded with bioactive materials exhibited antibacterial and remineralizing properties. They also enhanced the physical, mechanical, and chemical adhesive properties. The 5% nano-chitosan/calcium phosphate with gallic acid primer showed the highest mineral contents, making it the most suitable option for enamel remineralization.



جامعة الموصل
كلية طب الاسنان

تأثيرات النانو كيتوسان المحمل بالمواد النشطة بيولوجياً من فوسفات
الكالسيوم وحامض الغاليك لتعزيز اعادة تمعدن المينا على بعض خصائص
برايمر لاصق تقويم الأسنان

أطروحة تقدمت بها

لارا رياض عبدالرحيم البناء

الى

مجلس كلية طب الاسنان/جامعة الموصل

كجزء من متطلبات نيل شهادة

دكتوراه فلسفة في علوم طب الاسنان

بأشراف

أ.د. فوزي حبيب جبرائيل

أ.د. علي راجح محمود

الخلاصة

الخلفية: يعد ظهور البقع البيضاء أحد أكثر الآثار الجانبية غير المرغوب فيها للعلاج التقويمي الثابت. وعلى الرغم من الجهود الوقائية المختلفة، إلا أن انتشارها يظل مرتفعاً بشكل ملحوظ عند فك الحاصرات التقويمية. لذلك، من الضروري تثبيط النشاط البكتيري المسبب للتسوس مع تعزيز إعادة تمعدن مينا الأسنان منزوعة المعادن من أجل منع وعلاج البقع البيضاء.

الأهداف: ان الهدف من هذه الدراسة هو إعداد وتقييم تأثير إضافة نانو كيتوسان محمل بمواد نشطة بيولوجياً (فوسفات الكالسيوم وحامض الغاليك لوحدهم او مجتمعة) بتركيزين مختلفين في برايمر تقويم الأسنان كعامل مضاد للبكتيريا وإعادة تمعدن مع الحفاظ على الخصائص الفيزيائية والميكانيكية والكيميائية للمادة اللاصقة لتقويم الأسنان.

المواد وطرق العمل: تم تحضير نانو كيتوسان محمل بمواد نشطة بيولوجياً (فوسفات الكالسيوم وحامض الغاليك لوحدهم وكذلك تأثير كلا المادتين ممزوجتين مع بعض) وبتراكيزين مختلفين 5% و 10% وإضافتهم إلى برايمر التقويم (Transbond™ XT) لتكوين برايمر لاصق معدّل. قارنت هذه الدراسة سبع مجموعات: المجموعة الأولى: (مجموعة السيطرة)، المجموعة الثانية: (5% نانو كيتوسان/ فوسفات الكالسيوم برايمر)، المجموعة الثالثة: (10% نانو كيتوسان/ فوسفات الكالسيوم برايمر)، المجموعة الرابعة: (5% نانو كيتوسان/ حمض الغاليك برايمر)، المجموعة الخامسة: (10% نانو كيتوسان/ حمض الغاليك برايمر)، المجموعة السادسة: (5% نانو كيتوسان/ فوسفات الكالسيوم + حمض الغاليك برايمر)، المجموعة السابعة: (10% نانو كيتوسان/ فوسفات الكالسيوم + حمض الغاليك برايمر). تم فحص البرايمر المعدّل باستخدام مطيافية تحويل فورييه بالأشعة تحت الحمراء (FTIR) والمجهر الإلكتروني الماسح للانبعاثات الميدانية/مطيافية تشتت الطاقة بالأشعة السينية (FESEM/EDX). علاوة على ذلك، تم تقييم قوة رابطة القص ومؤشر بقايا المادة اللاصقة ودرجة تحويل المونومر، وقابلية البلل، وسلوك إطلاق حامض الغاليك وفوسفات الكالسيوم، والخصائص المضادة للبكتيريا ضد *S. mutans* و *L. acidophilus* وتقييم إعادة تمعدن مينا الأسنان منزوعة المعادن عن طريق المجهر الإلكتروني الماسح (FESEM) للكشف عن ترسب المعادن وشكل بلورات الهيدروكسيباتيت والتحليل الطيفي

بالأشعة السينية المشتتة للطاقة (EDX) لقياس نسبة الكالسيوم والفوسفات ونسبة الكالسيوم/الفوسفور.

النتائج: لم يظهر البرايمر التقويمي أي تغييرات كيميائية وبنوية عند إضافة النانو كيتوسان المحمل بالمواد النشطة بيولوجيًا والموزع بشكل متجانس داخله. أظهرت نتائج قوة رابطة القص ودرجة تحويل المونومر زيادة في قيمها مع وجود اختلافات كبيرة بين المجموعات، ولم يتم ملاحظة أي اختلاف كبير فيما يتعلق بكمية المادة اللاصقة المتبقية وقياسات زاوية التلامس بين المجموعات. بالإضافة إلى ذلك، أظهر برايمر تقويم الأسنان المعدل نشاطا كبيرا مضادا للبكتيريا بشكل كبير ضد *S. mutans* و *L. acidophilus* وخاصة مجموعة البرايمر المعدل ب (10% نانو كيتوسان / فوسفات الكالسيوم + حمض الغاليك). علاوة على ذلك، أظهرت مجموعة البرايمر المعدل ب (5% نانو كيتوسان / فوسفات الكالسيوم + حمض الجاليك) أعلى نسبة وزن للكالسيوم والفوسفات ونسبة الكالسيوم / الفوسفور من المجموعات الأخرى. أظهرت نتائج إطلاق فوسفات الكالسيوم وحمض الغاليك من البرايمر المعدل إطلاقا بطيئا ومستمرًا على مدار الأسابيع الأربعة مع وجود فرق كبير بين مجموعات 5% و 10% في كل اسبوع. أكدت عملية إطلاق المعادن على القابلية المضادة للبكتيريا وإعادة التمدن لمجموعات البرايمر المعدلة. تم تحديد الفرق المعنوي عند ($P \leq 0.05$).

الاستنتاج: كشفت هذه الدراسة المختبرية أن جميع مجموعات البرايمر التقويمية المعدلة باستخدام نانو كيتوسان محملة بالمواد النشطة بيولوجيًا تملك خصائص مضادة للبكتيريا وإعادة التمدن. بالإضافة إلى ذلك، فإنها تعمل على تحسين الخصائص الفيزيائية والميكانيكية والكيميائية للمادة اللاصقة. ومن بينها، أظهرت مجموعة البرايمر المعدل ب 10% نانو كيتوسان/فوسفات الكالسيوم + حامض الغاليك أقوى نشاط مضاد للبكتيريا في المقابل أظهرت مجموعة البرايمر المعدل ب 5% نانو كيتوسان/فوسفات الكالسيوم + حامض الغاليك أعلى فعالية لإعادة التمدن ، لذا فهي أكثر ملاءمة لعلاج آفات البقع البيضاء.