



جامعة الموصل
كلية التربية للنبات
قسم الكيمياء

إستخدام المخلفات الكبريتية من كبريت المشراق كمادة أولية في تحضير الكبريت النانوي

بدور كمال محمد صادق

رسالة الماجستير
علوم في الكيمياء

بإشراف

الخبير الدكتور

مطيع عبيد عبدالله الجبوري

الدكتور

ثائر عبد هلو

2021م

1443هـ

المستخلص بلغة الرسالة

تهدف هذه الدراسة إلى توظيف مخلفات الطريقة الحرارية لتنقية الكبريت المنجمي في المشرق والمعروفة بـ Blow Down بعد دراستها في تحضير أملاح متعدد الكبريتيد وأملاح الثايو كبريتات لأيونات الصوديوم واليوتاسيوم واستخدام هذه الاملاح في تحضير جزيئات الكبريت النانوي ، وقد تمت هذه الدراسة على النحو التالي:

1- تم دراسة مخلفات الـ Orthorombi و (19.1% وزناً) مادة كاربو-كبريتية تعرف تجارياً بالكارسول (Carsul) تكون بشكل تراكيب نانوية ضمن المخلفات وذات مدى حجم خبيبي (29.77-57.31) نانو متر ولا معيني Orthorombi و (19.1% وزناً) مادة كاربو-كبريتية تعرف تجارياً بالكارسول (Carsul) تكون بشكل تراكيب نانوية ضمن المخلفات وذات مدى حجم خبيبي (29.77-57.31) نانو متر ولا يمكن فصل هذه المادة بطرائق الفصل التقليدية.

2- تم استخلاص الكارسول من مخلفات البلوداون بوساطة CS_2 , NaOH, KOH, Ca(OH) $_2$ ودرستها بوساطة SEM, XRF, BET, XRD. واتضح أن تركيبها مشابه للمواد الكاربونية غير المتبلورة ومواد كاربوكبريتية التي يكون تركيبها بشكل طبقات ذات تراكيب نانوية مسامية إذ بلغت المساحة السطحية (8.2 ملم 2 /غم).

3- نظراً لإحتواء مخلفات البلوداون على نسبة عالية من الكبريت العنصري ومواد شبيهة خاملة إتجاه تفاعل الكبريت مع $Ca(OH)_2$, NaOH, KOH. تم إستخدام هذه المخلفات في تحضير محاليل أملاح متعدد كبريتيد الصوديوم واليوتاسيوم والكالسيوم بتراكيز (23.66، 18.44، 9.22%) على التوالي واستخدمت هذه الأملاح في تحضير جزيئات الكبريت النانوي بشكل مسحوق ومعلق.

وفي تحضير أملاح ثايو كبريتات الصوديوم واليوتاسيوم والكالسيوم بوساطة الأوكسدة الهوائية وبالتسخين إلى درجة (80) م $^{\circ}$ وكان تركيز هذه المحاليل على التوالي (0.09, 0.1, 0.025) بوحدة مكافئ/لتر.

4- أستخدمت محاليل متعدد كبريتيد الصوديوم واليوتاسيوم والكالسيوم وبإضافة كميات من MI حامض الهيدروكلوريك في تحضير الكبريت النانوي وكانت نسبة الإسترجاع هي (76.23، 57.6، 32.0%)

كما تم إستخدام حوامض (HCl, CH_3COOH, H_2SO_4) بوجود مثبثات وعدم وجود مثبثات (كبريتات لورابل الصوديوم ومنظف تجاري وصبغ تجاري) لحزيتات الكبريت النانوية وبالتخفيف بنسبة (1:1) حجماً تم الحصول على جزيئات كبريت نانوي بأحجام مختلفة ودراسة جميع النماذج بوساطة SEM وإختبار نموذج تم دراسته بوساطة XRD وتبين أن التركيب البلوري هو معيني Orthorombic ودراسة المساحة السطحية بطريقة BET للكبريت النانوي ومقارنته مع نموذج كبريت زراعي تجاري.

وتبين أن المساحة السطحية تضاغت ثنائي مرات عن الكبريت الزراعي التجاري.

5- أستخدمت أملاح متعدد كبريتيد الصوديوم واليوتاسيوم والكالسيوم وثايو كبريتات الصوديوم المختبرية وأملاح ثايو كبريتات الصوديوم واليوتاسيوم والكالسيوم المحضرة بوجود حوامض ذات تركيز امولاري من (حامض الهيدروكلوريك والخليك والكبريتيك) وتحديد الظروف المثلى للحصول على محلول معلق بإستخدام الصبغ ووجدنا أن (0.6غم) صبغاً لكل 100 مل محلولاً هي أفضل نسبة، وإستخدام مواد مثبثة (كبريتات لورابل الصوديوم ومنظف تجاري والصبغ التجاري) تمكنا من تحضير محاليل عاققة مستقرة ذات أحجام نانوية مختلفة وبشكل كروي التي يمكن إعادتها إذا ترسبت بالرج.

6- أستخدمت طريقة جديدة في تحضير جزيئات الكبريت النانوي بتخفيف حجوم قليلة (0.1-1) مل في لتر واحد من الماء المقطر ويوجد 0.6غم من الصبغ التجاري وتم الحصول على محاليل معلقة مستقرة لمدة فاقت 30 يوماً وتم دراسة مدى الحجم الحبيبي لتراكيز (0.1-0.2) مل كالاتي (17-13.34) (35.36-16.75) نانومتر وكان التركيب البلوري الكبريت النانوي من نوع الكبريت المعيني كما بين ذلك XRD. إتسمت هذه الطريقة بالسهولة وعدم إتبعث غازات كبريتية ضارة.

7- تم إسترداد الكبريت النانوي من غاز كبريتيد الهيدروجين بفاعله مع محلول (حامض المالك- $FeCl_3$) و (0.6) غم من الصبغ التجاري وكان مدى الحجم الحبيبي للكبريت النانوي (89.15-56.59) نانومتر.

توقيع مسؤول الدراسات العليا

أ.م.د. محمد اسماعيل محمد

تأييد المشرف

أويد بان مستخلص الاستمارة مطبق للمستخلص في الرسالة

الإسم: م.د. ثامر عبد هلو
الخبير الدكتور مطيع عبيد عبد الله الجبوري

Abstract

This study aims to employ the remnants of the thermal method for the purification of mining sulfur in Al-Mishraq, known as Blow Down, after studying it in the preparation of polysulfide salts and thiosulfate salts for sodium and potassium ions, and using these salts in the preparation of NPS, and this study was carried out as follows:

1-BlowDown residues were studied chemically and spectroscopically by means of SEM, XRD, and EDS, and it was found that these wastes consist of (80.1% wt/wt) elemental sulfur with orthorombic crystal structure and (19.1%) carbo sulfur material commercially known as carsul.) It is in the form of nanostructures within the residues and has a grain size range (57.31 - 29.77 nm) and this material cannot be separated by conventional separation methods.

2-Carsol was extracted from Blow Down residues by CS₂, NaOH, KOH, Ca(OH)₂ and studied by XRD, XRF, BET, SEM and it was found that its composition is similar to the amorphous carbonate and carbocrystalline materials whose structure is in the form of layers with porous nanostructures. The surface area was (8.2).

3- Due to the high percentage of elemental sulfur and semi-inert sulfur reaction NaOH, KOH, Ca(OH)₂ sulfur residues. These residues were used in the preparation of sodium, potassium and calcium polysulfide salt solutions with concentrations (23.66, 18.44 , 9.22 %), respectively, and these salts were used to prepare nanoparticles of sulfur in the form of powder and suspension.

In the preparation of sodium, potassium and calcium thiosulfate salts by means of aerobic oxidation and heating to 80°C, the concentration of the solutions of these solutions was (0.09, 0.1, 0.025) in eq/L units.

4-Polysulfide solutions of sodium, potassium, and calcium were used, with the addition of quantities of M1 acid and hydrochloric acid, in the preparation of nano-sulfur, and the recovery rate was (76.23, 57.6, 32.0%).

Also, acids (HCl, CH₃COOH, H₂SO₄) were used in the presence and absence of granular sulfur nanoparticles (sodium lauryl sulfate, commercial detergent and commercial gum) and at a ratio of (1:1). XRD study and it was found that the crystal structure is rhombic orthorombic and the surface area study by BET method of nano sulfur and compared with a commercial agricultural sulfur model.

It was found that the surface area multiplied eight times that of commercial agricultural sulfur.

5- Sodium, potassium and calcium polysulfide salts were used, and laboratory sodium thiosulfate and sodium, potassium and calcium thiosulfate salts prepared in the presence of acids of concentration M1 (HCl and CH₃COOH) were used and the optimum conditions were determined to obtain a suspension solution using gum. It was found that (0.6g) gum per 100 ml solution It is the best ratio, and by using sodium lauryl sulfate dispersants, commercial detergent, and commercial gum, we were able to prepare stable suspension solutions with different nanosizes and spherical shapes that can be returned if precipitated by shaking.

6- A new method was used to prepare nano-sulfur particles by diluting small volumes (0.1-1) milliliters in one liter of distilled water and in the presence of 0.6g of commercial gum, and stable suspension solutions were obtained for more than 30 days. The range of particle size of concentrations (0.1-0.2) was studied.) ml as the following (17-13.34 nm) (35.36-16.75 nm) and the crystal structure of nano sulfur was of the

rhombic sulfur type as shown by XRD. This method was easy and did not emit harmful sulfur gases.

7- Nano-sulfur was recovered from hydrogen sulfide gas by reacting it with (malic acid- FeCl_3) solution in the presence of (0.6g) of commercial gum, and the granular size range of nano-sulfur was (89.15-56.59m).

University of Mosul
College of Education for Girls
Chemistry Department



**The Use of Sulfur Residues from Mishraq
Sulfur as a Raw Material in the Preparation
of Nanoscale Sulfur**

Budoor Kamal Mohammad Sadiq

Master Thesis
Sciences in Chemistry

Supervised by

Dr.

Dr. expert

Thaer Abd Hello

Mote'a Ubaid Abdullah Al-jbouri

1443 A.H.

2021 A.D.